

# *Standing-wave excited XES and RIXS: new tools for buried interface studies*



**M. Watanabe<sup>1,2</sup>, B.C. Sell<sup>2,3</sup>, S.-H. Yang<sup>4</sup>, B.S. Mun<sup>2,5</sup>,  
N. Mannella<sup>3,6</sup>, L. D. Pham<sup>2,3</sup>, S.B. Ritchey<sup>2,3</sup>,  
A. Nambu<sup>2,7</sup>, F. Salmassi<sup>2</sup>, J. Guo<sup>5</sup>, J.B. Kortright<sup>2</sup>,  
S.S.P. Parkin<sup>4</sup>, and C.S. Fadley<sup>2,3</sup>**



<sup>1</sup>RIKEN/Spring8, Harima Institute, Sayo, Hyogo, 679-5148, Japan

<sup>2</sup>Materials Sciences Division, Lawrence Berkeley National Laboratory,  
Berkeley, CA 94720

<sup>3</sup>Dept. of Physics, Univ. of California Davis, Davis, CA, 95616 USA

<sup>4</sup>IBM Almaden Research Center, San Jose, CA 95120

<sup>5</sup>Advanced Light Source, Lawrence Berkeley National Laboratory,  
Berkeley, CA 94720

<sup>6</sup>Dept. of Applied Physics, Stanford University, Stanford CA 94305



<sup>7</sup>Dept. of Chemistry, Univ. of Tokyo, Hongo,  
Bunkyo-ku, Tokyo, Japan




The Advanced  
Light Source

# Outline

- Intro. to standing wave-wedge technique for probing buried interfaces:  
Prior example - Photoemission results for Fe/Cr;  
Fe-2p, -3p, Cr-2p, -3p photoemission, incl. MCD
  
- New results: XES/RIXS for Fe/Cr:  
Fe-L $\alpha\beta$  emission intensities, incl. MCD




## MULTI-TECHNIQUE SPECTROMETER/ DIFFRACTOMETER (MTSD)




Permits using all relevant soft x-ray spectroscopies on a single sample:  
PS, PD, PH; XAS (e<sup>-</sup> or photon detection), **XES/RIXS in MCD, MLD**

Multilayer  
mirror =  
Standing wave  
generator:

$$d_{ML}$$




# The Standing Wave-Wedge Method



# Probing Buried Interfaces with Soft X-ray Standing Waves: Core PS Spectra

Fe/Cr: a prototypical system for giant magneto-resistance

S.-H. Yang, B.S. Mun et al.,  
Surf. Sci. Lett. 461, L557 (2000);  
Phys. Cond. Matt. 14, L406 (2002)



-  $n(h\nu) =$

$$1 - \delta(h\nu) + i\beta(h\nu)$$

- variable polarization

- multiple reflection/refraction

- exact treatment of interlayer intermixing a/o roughness

- electric field at  $i$ -th layer:

$$I(z) = |E_i^+(z) + E_i^-(z)|^2$$

**Photoemission:**


- differential cross section

- inelastic attenuation

- surface refraction


**X-ray emission:**

- fluorescence yield




*Experimental + Calculated  
Photoemission Yield Ratio  
 $I(Fe\ 3p)/I(Cr\ 3p)$  from Fe/Cr wedge  
on standing-wave multilayer*

**Incidence Photon Angle Scan**  
**Sample angle scan**  
**for rocking curve**




S.-H. Yang, B.S. Mun et al.,  
Surf. Sci. Lett. 461, L557 (2000);  
Phys. Cond. Matt. 14, L406 (2002)

**Rocking curves**





**Sample scan =  
Cr thickness depend.**



# Fe and Cr 2p magnetic circular dichroism--probe of y-axis magnetization


Fe and Cr 2p MCD data from Fe/Cr wedge/multilayer

**Cr magnetization  
Is antiparallel to  
Fe; systematic  
variation of MCD  
strengths vs  $d_{cr}$**




S.-H. Yang, B.S. Mun et al.,  
Surf. Sci. Lett. 461, L557 (2000);  
Phys. Cond. Matt. 14, L406 (2002)

Plus similar results for Fe 3p and Cr 3p




**Fitting core PS experiment to XRO theory: non-destructive, depth-resolved determination of composition and magnetization profiles**




S.-H. Yang, B.S. Mun et al.,  
Surf. Sci. Lett. 461, L557 (2000);  
Phys. Cond. Matt. 14, L406 (2002)

# The Standing Wave-Wedge Method






# Standing wave excitation of x-ray emission/RIXS in a multilayer magnetic structure

Sample angle scan  
for rocking curve





Sample position scan  
over wedge thickness







*Experimental + Calculated  
X-Ray Emission Yield Ratio  
 $I(\text{Fe L}\alpha\beta)/I(\text{Cr L}\alpha\beta)$  from Fe/Cr wedge  
on standing-wave multilayer*



**RIXS with Standing Wave Excitation:  
Fe-L x-ray emission, L2 edge excitation, MCD  
Z-position dependence**




$$\text{MCD} = \frac{2\{I(\text{RCP}) - I(\text{LCP})\}}{\{I_{\max}(\text{RCP}) + I_{\max}(\text{LCP})\}}$$

# RIXS with Standing Wave Excitation: Fe-L x-ray emission, MCD L2 edge excitation Z-position (Cr-thickness) dependence



Phase shift → bottom of Fe layer  
not magnetized, at least along y?




Not magnetized?  
FeCr intermixing?

Sine curve


MCD via smoothed data

MCD via Gaussian fit




## Fe-L emission peak intensities







## Fe-L $\alpha$ MCD



# XRO modeling of intensities and MCD phase shift






**XRO modeling of  
Intensity / MCD  
phase shift**





# Summary

- First x-ray emission/RIXS results using standing wave-wedge method: Fe/Cr-wedge/multilayer--  
Fe-L $\alpha\beta$  emission intensities and MCD
- Fe-L/Cr-L intensity ratios (rocking curves and sample scans) fit well with XRO calculations
- Strong modulation of Fe-L RIXS and Fe-L RIXS MCD with sample scans → phase shift of  $11 \pm 2 \text{ \AA}$
- Phase shift is reproduced by XRO calculations with Fe-Cr interdiffusion and reduced magnetization in interface
- Suggests many interesting future applications of standing wave-wedge approach with XES/RIXS detection



## STANDING-WAVE EXCITED SPECTROSCOPY--FUTURE POSSIBILITIES

- Other material pairs in multilayer ( $B_4C/W$ ,  $Al_2O_3/Pt, \dots$ ) + epitaxial multilayers → epitaxial samples
  - Smaller periods (to  $\sim 25\text{-}30 \text{ \AA}$ ) → smaller SW period, better resolution
  - Lower  $h\nu_{inc}$  → higher Bragg angles → perpend. component of  $M$
  - X-ray emission → deeper layers, more sensitivity to SW position



P. Fischer  
G. Denbeaux  
ALS XM-1